

Excellent Integrated System Limited


Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

[Desco](#)
[37630](#)

For any questions, you can email us directly:

sales@integrated-circuit.com



Features

- Used to transport or store ESD Sensitive items
- Rotating steel wire arms- when rotated in, totes are stackable even full of product, saving valuable space and enhancing productivity when moved
- Rotating steel wire arms - when rotated out, totes can nest, saving space when when storing
- Great container for Kanban

RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Protektive Pak Inc. letter on-line at ProtektivePak.com.

Item No.	O.D. Top Size - L x W x D	I.D. Bottom Size - L x W x D
37630	18 x 12 x 6	15 x 8-3/4 x 6
37631	27-1/4 x 12 x 6	24-1/2 x 8-3/4 x 6
37632	27-1/4 x 18 x 6	24-1/2 x 15 x 6

SPECIFICATIONS

Properties

Electrostatic Decay

Surface Resistivity

Surface Resistivity, Low R.H. Cut-off

High-Voltage Discharge Resistance

Static Shielding

Charged Device Model (CDM) Safety

Current-Carrying Hazard

Corrosivity

Antistat Transfer

Water & Isopropyl Alcohol Extraction

Tests for Antistat Permanence

Sloughing Test

Recyclability

Biodegradability

Volume Conductivity

Shelf Life

Typical Values

0.01 seconds at 72°F and 11.8% R.H.

$10^7 - 10^8$ ohms/sq. after 11 days at 68°F and 12% R.H. for surface. $10^3 - 10^4$ ohms/sq. for buried shielding layer 4% R.H.

Failure rate 0/5 (no oxide damage in five consecutive tests)

99.9% attenuation at 10kV; 99.6% attenuation at 30kV

RTG $>10^7$ ohms at 86% R.H. or less

10^3 mA at 110V; 10^3 mA at 220V

Contains 1-3 ppm reducible sulfur

No transfer

Surface resistivity $10^8 - 10^9$ ohms/square at 74°F and 36% R.H.

Negligible surface damage at 10 cycles and $<5\%$ of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Biodegradation in or on moist soil

Conductivity from wall to wall as well as across surface to assure permanence of the antistatic property

Indefinite

Test Procedures/Method

FED-STD-101, Method 4046

ASTM D257

Rockwell International Test Report of December 20, 1991

Rockwell International Test Report of December 20, 1991

EIA 541, appendix E, capacitive probe test

Rockwell International Test Report of December 20, 1991

ESD from A to Z

FED-STD-101, Method 3005 for reducible sulfur

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in America

STACKABLE NESTING TOTES

PROTEKTIVE PAK

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578, FAX (909) 363-7331
www.protektivepak.com

DRAWING NUMBER
37630

DATE:
5/06