

### **Excellent Integrated System Limited**

Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

<u>3M</u> AL-36FR X 1

For any questions, you can email us directly: sales@integrated-circuit.com



## **3M**

# Tape AL-36FR

## Polyester Film-Laminated Aluminum Foil with Conductive Acrylic Adhesive

### **Data Sheet**



#### **Product Description**

3M<sup>™</sup> Tape AL-36FR consists of polyester filmlaminated aluminum foil and unique electrically conductive pressure-sensitive acrylic adhesive.

- PET-laminated aluminum foil backing
- Conductive acrylic adhesive
- Supplied on a removable liner for easy handling and die cutting
- UL recognized for flame retardancy per UL 510, Product Category OANZ2, File E166244.

3M Tape AL-36FR is available in standard and custom widths and lengths. Standard length is 100 m.

- Widths from 6 mm to 500 mm
- Longer lengths up to several times normal length, dependent upon width. Check with a 3M sales representative.

#### **Applications**

3M Tape AL-36FR is typically used for applications requiring excellent electrical conductivity from the application substrate through the adhesive to the foil backing and for insulation on top of the foil backing. Common uses include grounding and EMI shielding in equipment, components, shielded rooms, etc.

#### **Shielding Effectiveness**

Many factors determine the true shielding effectiveness of a shielding tape, including type and thickness, adhesive strength, degree of contact, smoothness of application surface, strength and frequency of the EMI signal, etc. However, using standard tests and fixtures, it is possible to determine a value for the attenuation

Properties	Typical Value
Type of Backing	PET-laminated aluminum foil backing
Type of Adhesive	Conductive acrylic adhesive
Total thickness (backing plus adhesive)	$0.06 \pm 0.005 \text{ mm}$
Adhesion to steel <sup>1</sup>	$1000 \text{ g}_{\text{f}} / 25 \text{ mm} (2.2 \text{ N} / 25 \text{ mm})$
Electrical resistance through adhesive <sup>2</sup>	$0.02~\Omega$ / $25~\text{mm}^2$
Shielding effectiveness <sup>3</sup>	Refer to attenuation chart


\* Footnotes: 1. ASTM D 1000 Test method

2. MIL-STD-202 Method 307

3. ASTM-D-4935 Test method



#### Shielding Effectiveness (Test method: ASTM D4935)



3M is a trademark of 3M Company.

#### **Important Notice**

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Warranty; Limited Remedy; Limited Liability. This product will be free from defects in material and manufacture as of the date of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, Indirect, special, Incidental or consequential regardless of the legal theory asserted.

#### **3M**

**Electrical Markets Division** 

6801 River Place Blvd. Austin, TX 78726-9000 www.3M.com/electrical/oem

Litho in USA © 3M 2004 78-8126-6587-1-A