

## **Excellent Integrated System Limited**

Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

<u>3M</u> 7993MP-3/4-CIRCLE

For any questions, you can email us directly: <u>sales@integrated-circuit.com</u>



# **ЗМ** Scotch<sup>тм</sup>

## Single Side Membrane Switch Spacer 7993MP

### **Product Data Sheet**

Updated:July 2000Supersedes:November 1994

Physical Properties Not for specification purposes	Carrier	1.0 Polyester		
	Adhesive	2.0 #200 "High Performance" Acrylic 90# Bleached Kraft		
	Liner			
	Shelf Life	24 months from date of manufacture by 3M if stored at room temperature condition in cool, dry and sun protected room.		
Features:	•	onmentally stable adhesive to resist UV. light, chemicals, and		
	<ul> <li>temperatures to 300°F (149°C).</li> <li>High cohesive strength of the adhesive withstands repeated stresses of switch actuation.</li> </ul>			
Applications	<ul> <li>Add a different thickness of adhesive to one side of a membrane switch to build a membrane switch spacer.</li> </ul>			
	• Designed for use as a substrate for membrane switch circuitry.			
	Hold metal domes in place.			
	Protect conductive leads.			



Date : July 2000 Single Side Membrane Switch Spacer 7993MP

Initial Adhesion Not for specification purposes	Dynamic Peel - 180° Peel (ASTM D-3330, PSTC3)	Stainless Steel N/10mm	3.6

Properties and Performance Not for specification purposes	Temperature Range	Low : -40°F (-40C) High Long Term (days/weeks) : 250°F (121°C). High Short Term (minutes/hours) : 300°F (149°C).
	Chemical Resistance	Solvent resistance is excellent when this product is properly applied to impervious materials. The adhesive resists softening through edge contact with mild acids, alkalis, oil, gasoline, Kerosene, JP-4 fuel and many other solvents. Not recommended for total immersion.
	Moisture & Humidity Resistance	No adverse effect on the bond after exposure to 100% Relative Humidity at 38°C.
	Bond Build Up	The bond strength of Scotch #200 Hi-Performance Acrylic adhesive increases as a function of time and temperature.
	U.V. Resistance	Adhesive is very resistant to oxidisation and ozone when exposed to air or sunlight (U.V.).

#### Processing

#### Die-cutting:

Steel rule or punch press die-cuttable.

#### **Roll Laminating:**

Use rubber over steel roll set up with firm application pressure. Make adhesive to substrate contact at nip area only to exclude air entrapment.

2



Date : July 2000 Single Side Membrane Switch Spacer 7993MP

#### **Other Considerations**

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.

To obtain adhesion, the bonding surfaces must be clean, dry, and smooth. Some typical surface cleaning solvents are isopropyl alcohol or heptane. Consult manufacturer's Material Safety Data Sheet for proper handling and storage of solvents.

Ideal tape application temperature range is 70°F (21°C) to 100°F (38°C) Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



**Tapes & Adhesives Group** 

3M United Kingdom PLC 3M House, PO Box 1, Market Place. Product Information : Tel 0870 60 800 50

3M Ireland 3M House, Adelphi Centre, Upper Georges Street, © 3M United Kingdom PLC 2000

Customer Service :

Tel (01) 280 3555

3