

# **Excellent Integrated System Limited**

Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

NessCap ESHSR-0003C0-002R7

For any questions, you can email us directly: <u>sales@integrated-circuit.com</u>



### Distributor of NessCap : Excellent Integrated System Limited

Datasheet of ESHSR-0003C0-002R7 - CAP 3F -10% +20% 2.7V T/H

Contact us: sales@integrated-circuit.com Website: www.integrated-circuit.com

### Datasheet - 2.7V / 3F Cell



#### **FEATURES**

- » High performance product with low RC time constant
- » Long lifetimes with over 500,000 duty cycles
- » Rated capacitance of 3F
- » Compliant with RoHS and REACH requirements

#### **SPECIFICATIONS**

		* Image is not to scale		
Electrical		ESHSR-0003C0-002R7		
Rated Voltage (V <sub>R</sub> ) at 65°C		2.7VDC		
Rated Voltage (V <sub>R</sub> ) at 85°C		2.3VDC		
Surge Voltage <sup>1</sup>		2.85VDC		
Rated Capacitance <sup>2</sup>		3F		
Canacitanaa Talaranaa	Max.	-10% / +20%		
Capacitance Tolerance	Avg. <sup>4</sup>	-5% / +5%		
DC-ESR <sup>3</sup>	Max.	55mΩ		
DC-ESR	Avg. <sup>4</sup>	40mΩ		
Max. Leakage Current <sup>5</sup>		0.005mA		
Maximum Continuous Current	at ∆T = 15°C	2.0A		
Maximum Commuous Current	at ∆T = 40°C	3.3A		
Maximum Peak Current, Non-repetitive <sup>6</sup>	at 65°C	3.4A		
Maximum Feak Current, Non-repetitive	at 85°C	2.9A		
Max. Stored Energy $(E_{max})$ at $V_{R}^{7}$	at 65°C	3.0mWh		
Max. Stored Energy (Emax) at VR	at 85°C	2.2mWh		
Usable Specific Power <sup>7</sup>	at 65°C	10.6kW/kg		
Usable Specific Power	at 85°C	7.7kW/kg		
Immediance Match / Crestific Davis"	at 65°C	22.1kW/kg		
Impedance Match / Specific Power <sup>7</sup>	at 85°C	16.0kW/kg		
Max. Gravimetric Specific Energy <sup>7</sup>		2.0Wh/kg		

Temperature	
Operating Temperature Range	<ul> <li>-40 ~ 65°C (up to 85°C with de-rated voltage)</li> <li>(ΔCAP&lt;5% and ΔESR&lt;300% of initial value measured at 25°C, with linear voltage de-rating to 2.3V @ 85°C)</li> </ul>
Storage Temperature Range	-40 ~ 70°C (storage without charge)

Life			
Endurance <sup>8,9</sup>	at 65°C, 2.7V	1,500 hours	
	at 85°C, 2.3V	1,000 hours	
Room Temperature (at V <sub>R</sub> and 25°C) <sup>8</sup>	10 years		
Cycle Life (at 25°C) <sup>8</sup>	500,000 cycles		
	(Cycled from $V_R$ to $1/2V_R$ using 100mA/F const. current with 10sec rest between		
	charge and discharge steps)		
Shelf Life	2 years		
	(Stored without charge at or under 70°C and under 40% RH)		

Safety & Certification	
RoHS	Compliant
REACH	Compliant
UL	Complies to 810A, Certificate No.: BBBG2.MH46340





#### **Distributor of NessCap : Excellent Integrated System Limited** Datasheet of ESHSR-0003C0-002R7 - CAP 3F -10% +20% 2.7V T/H

Contact us: sales@integrated-circuit.com Website: www.integrated-circuit.com




## Datasheet - 2.7V / 3F Cell



#### THERMAL

Characteristics	ESHSR-0003C0-002R7
Typical Thermal Resistance, Rth (Housing)	67°C/W
Typical Thermal Capacitance, Cth	1.3J/°C
Cont. Current to $\Delta T = 15^{\circ}C$	2.0A
Cont. Current to $\Delta T = 40^{\circ}C$	3.3A

#### PHYSICAL



Dimensions	ESHSR-0003C0-002R7
D (+0.5)	8 mm
L (+1.5)	20 mm
H1 (Min.)	15 mm
H2 (Min.)	19 mm
d (±0.05)	0.6 mm
A (±0.5)	3.5 mm
Nominal Weight	1.5 g



#### Distributor of NessCap : Excellent Integrated System Limited

Datasheet of ESHSR-0003C0-002R7 - CAP 3F -10% +20% 2.7V T/H

Contact us: sales@integrated-circuit.com Website: www.integrated-circuit.com




### Datasheet - 2.7V / 3F Cell



#### NOTE


- 1. Surge Voltage
  - > Absolute maximum voltage, not repeated and for no longer than 1 second.
- 2. Rated Capacitance
  - > Constant current charge with 10mA/F to  $\mathrm{V}_{\mathrm{R}}$
  - > Constant voltage charge at  $V_{\text{R}}$  for 5min
  - > Constant current discharge with 10mA/F to 0.1V



- Where  $\upsilon_1$  is the measurement starting voltage,  $\rm 0.8 \times V_R$  (V);  $\upsilon_2$  is the measurement end voltage,  $0.4 \times V_{\text{R}}$  (V);  $t_1$  is the time from discharge start to reach  $v_1$  (s);
  - $t_2$  is the time from discharge start to reach  $\boldsymbol{\nu}_2$  (s);
  - I is the absolute value of the discharging current (A).

#### 3. ESR (Equivalent Series Resistance)

- > ESR<sub>DC</sub>
  - Constant current charge to  $V_R$
  - Constant voltage charge at  $V_R$  for 5min
  - Constant current discharge to 0.1V



- $R_d$  is the ESR<sub>DC</sub> ( $\Omega$ ); Where  $\Delta v$  is the voltage drop for 10ms (V); I is the discharge current (A).
- 4. Average (or Typical)
- > Percentage spread that may be present in one shipment
- 5. Leakage Current
- > The capacitor is charged to the rated voltage at 25°C.
   > Leakage current is the current at 72hours that is required to keep the capacitor charged at the rated voltage

- 6. Max. Current
- > Current for 1sec discharging from rated voltage to half rated voltage under constant current discharging mode.

$$I_{Max.} (A) = \frac{\frac{1}{2}V_R}{\Delta t / C + R_d}$$

 $\Delta t$  is the discharge time (sec) and  $\Delta t$  is 1 sec in this case; Where C is the capacitance (F);  $R_d$  is the ESR<sub>DC</sub> ( $\Omega$ );  $V_R$  is the rated voltage (V).

- > Max. Current should not be used in normal operation and is only provided as a reference value.
- 7. Energy & Power
  - $\frac{1}{2}CV_{R}^{2}$ > Max. Stored Energy at  $V_R$  = 3600

Where C is the capacitance (F);  $V_R$  is the rated voltage (V).

- $0.12 \cdot V^2$ > Usable Specific Power, IEC 62391-2 (W/kg) =  $\frac{0.12}{ESR_{DC} \cdot Mass}$
- $0.25 \cdot V^2$ > Impedance Match Specific Power (W/kg) =  $\frac{0.23}{ESR_{DC} \cdot Mass}$

- > Gravimetric Specific Energy (Wh/kg) =  $\frac{E_{Max.}}{Weight}$
- 8. Lifetime
- > End-of-Life Conditions
  - Capacitance: -30% from rated min. value
    - ESR: +100% from max. ESR value

9. Endurance

- > Conditions  $65 \pm 2^{\circ}$ C or  $85 \pm 2^{\circ}$ C Temperature:
  - Test duration: 1500 (+48/-0) h
  - Applied voltage:  $V_R \pm 0.02V$
  - Capacitance and ESR measurement are made at 25°C

10. Mounting

- > Provide properly spaced holes for mounting according to the cell dimensions as to minimize leads being mechanically stressed.
- > Do not place any copper patterns, including the ground pattern, or through-hole via underneath the cell or on the underside of the PCB (if a double-sided PCB is used) as the electrolyte inside the cell, if it should leak, can corrode, short-circuit, the patterns and/or damage other components nearby. Spacing of 1mm or more should be provided in between the footprint of the cell and the nearest copper pattern.
- > Protective coating of components nearby on the PCB is recommended to reduce the risk of them being damaged in an event of electrolyte leakage.
- > Provide at least 2mm clearance above the safety vent and do not position
- anything above the safety vent that may be damaged by vent rupture.
   Place cells on the PCB taking into account that the cells may not be completely hermetic during its lifetime. Electrolyte vapor and gases generated during normal use may escape the package during normal operation.
- > Soldering recommendation for small and medium size cells available on www.nesscap.com under Support > Download.

The contents of this document are subject to change without notice. Values presented are thought to be accurate at the time of writing. Nesscap does not guarantee that the values are error-free, nor does Nesscap make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. For more information, you can reach us at one of following contacts

Nesscap Energy Inc. Suite 3800, Royal Bank Plaza, South Tower, 200 Bay Street, P.O. Box 84, Toronto, Ontario. M5J 2Z4	Nesscap Energy Inc. S24040 Camino Del Avion #A118, Monarch Beach, California, 92629	Nesscap Co., Ltd. 17, Dongtangiheung-ro 681beon-gil, Giheung-gu, Yongin-si, Gyeonggi-do	Nesscap China Room 1608, Block N, Cangson Building, Chegonmiao, Futian District, Shenzhen City, PR.C	Nesscap Energy EASTERN EUROPE 10A, prospect 60-letiya Oktyabrya Moscow, 117036	Nesscap Energy GmbH Beerengarten 4 D-86938 Schondorf
CANADA	USA	REPUBLIC OF KOREA	CHINA	RUSSIA	GERMANY
marketing@nesscap.com			info@nesso	ap-energy.de	