

Excellent Integrated System Limited

Stocking Distributor

Click to view price, real time Inventory, Delivery & Lifecycle Information:

[MG Chemicals](#)
[RTV31-1P](#)

For any questions, you can email us directly:

sales@integrated-circuit.com

RTV Silicones



ALL MG PRODUCTS ▾

Jump to Product Number



[Accessories](#)

[Adhesives](#)

[Brushes](#)

[Cleaners / Degreasers](#)

[Contact Cleaners](#)

[Desoldering Braid](#)

[Dusters & Circuit Coolers](#)

[EMI / RFI Shielding](#)

[Epoxies](#)

[Flux and Flux Remover](#)

[Glass & Screen Cleaners](#)

[Isopropyl Alcohol](#)

[Lead Free Solder](#)

[Lubricants](#)

[Potting & Encapsulating](#)

[Protective Coatings](#)

[Pens](#)

[Prototyping Materials](#)

[RTV Silicones](#)

[Soldering/desoldering](#)

[Specialized Cleaners](#)

[Swabs](#)

[Thermal Management](#)

[Thermally Conductive](#)

[Adhesives](#)

[Wipes](#)

RTV Silicones by **2-Part Potting/Encapsulating Compound** **RTV31**

► **SPECIAL ORDER**

► **BUY NOW**

Primary Characteristics

- Red pourable
- Condensation cure
- **Extreme high temp**
- Useful to 260°C (500°F)
- Primer required

Use for:

- Potting surge protectors on telephone poles
- Potting industrial filters
- High temp. electrical potting applications
- Mechanical protection

silicone rubber compound for electrical potting and mechanical applications for high temperature resistance and low viscosity with variable work times and cure rates. Elastomeric properties range from -54°C to 260°C continuously, to 316°C for short periods. Requires primer for adhesion. The product comes complete with catalyst DBT. Specialized catalysts are available upon request.

Available Sizes

Catalog Number	Sizes Available	Description
RTV31-1P	1 pint	pail
RTV31-1G	1 gallon	pail
RTV31-5G	5 gallon	pail
RTV31 requires a primer. Visit our primer guide for details.		

Specifications

Use	Potting & Encapsulating
Special Feature	High Temperature
NSN	8030-00-11-2762
Cross Reference	RTV31
Uncured Properties	
Consistency	Flowable
Color	Red
Specific Gravity	1.42
Pot Life	2 hours
Cure Through Time	24 hours
Useful Temp. Range	-54°C to 260°C (-65°F to 500°F)
Cured Properties - MECHANICAL	
<u>Hardness</u>	54 (Shore A)
Tensile Strength	5.98 MPa (870 psi)
Elongation	170%
Cured Properties - ELECTRICAL	
Volume Resistivity	1.6 x 10 ¹⁴ ohm · cm
Dielectric Strength	17 kV/mm (430 V/mil)
Dielectric Constant	4.4 @ 1000Hz
Cured Properties - THERMAL	

Technical Support
for RTV Silicones

☎ 1-800-255-8886

M.G. Chemicals Disclaimer
for RTV Silicones >

Locate Distributor >

Quick Links

- [MSDS](#)
- [Catalyst options/MSDS](#)
- [Primer options/MSDS](#)
- [Specifications](#)
- [Available Sizes](#)

Related products:

- [RTV21](#)
- [RTV31](#)
- [RTV60](#)
- [RTV88](#)
- [RTV560](#)
- [RTV566](#)
- [RTV577](#)
- [RTV630](#)
- [RTV656](#)

Resources

- [Selection Guide >](#)
- [One Part Chart](#)
- [Two Part Chart](#)

Find by Application

- [General Purpose >](#)
- [Aerospace >](#)
- [Marine >](#)
- [High Performance Assembly >](#)
- [Electronics >](#)
- [Thermal Conductivity >](#)
- [High Temperature >](#)
- [Low Temperature >](#)



Thermal Conductivity	0.31 W/m · °K
Thermal Expansion	20 x 10 ⁻⁵ cm/cm °C
	(11 x 10 ⁻⁵ in/in °F)
Other	
Viscosity (@ 25°C)	25,000 cps
Mix ratio (by weight)	100:0.5

[Return to top](#) ^